



PSI™ FIBERSTRAND™ REPREVE 225

SYNTHETIC MICROFIBER

PRODUCT INFORMATION

PACKAGING

1.0 lb (0.45 kg) and 1.3 lb (0.67 kg) water soluble bags. Special packaging configurations are also available upon request.

SHELF LIFE

3 years in original, unopened package

SPECIFICATIONS/COMPLIANCES

ASTM C1116

ASTM D7508

ICC Acceptance Criteria AC32

TECHNICAL INFORMATION

Material: REPREVE Polyester

Specific Gravity: 1.34

Typical Dosage Rates:

0.5 lbs/yd³ (0.3 kg/m³)

Available Lengths:

¼" (6 mm)

Melt Point: 475°F (245°C)

Electrical/Thermal Conductivity: Low

Water Absorption: Negligible

Acid and Alkali Resistance: Excellent

Color: Light Gray

* Tensile strength and aspect ratio are not applicable for micro fibers based on ASTM D7508.

DESCRIPTION

PSI FIBERSTRAND REPREVE 225 is a fine denier monofilament synthetic microfiber for concrete reinforcement manufactured from sustainably resourced polyester that complies with ASTM C1116 (Standard Specification for Fiber Reinforced Concrete and Shotcrete) and is specifically designed to help mitigate the formation of plastic shrinkage cracking in concrete. Typically used at a dosage rate of 0.5 lb/yd³ (0.3 kg/m³), PSI FIBERSTRAND REPREVE 225 microfibers will greatly reduce plastic shrinkage cracking when compared to plain concrete. PSI FIBERSTRAND REPREVE 225 microfibers also comply with applicable portions of the International Code Council (ICC) Acceptance Criteria AC32 for synthetic fibers. For every pound of PSI FIBERSTRAND REPREVE 225, up to 10 plastic bottles are diverted from landfills and instead used to reinforce concrete.

PRODUCT CHARACTERISTICS

FEATURES & BENEFITS

- Controls and mitigates plastic shrinkage cracking
- Reduces segregation and bleed-water
- Provides three-dimensional reinforcement against micro-cracking and spalling
- Increases surface durability and improves fire, impact and abrasion resistance
- Reduction of in-place cost versus wire mesh for non-structural temperature/shrinkage crack control
- Easily added to concrete mixture at any time prior to placement
- Sustainably resourced with low environmental impact
- Over 300 million fibers per pound

PRIMARY APPLICATIONS

- Slabs-on-grade, sidewalks, driveways, parking lots, curb work, overlays and toppings
- Footings, foundations, walls and tanks
- Stucco applications
- Precast and prestressed structures
- Shotcrete and slope paving
- Spalling control and fire protection
- Composite steel deck
- Stamped and colored concrete

PRECAUTIONS/LIMITATIONS

- Use of fibers may cause an apparent loss in measured slump of concrete. This may be offset with the use of a water reducing admixture if necessary.
- Fibers should never be added to a “zero-slump” concrete. Ensure a minimum concrete slump of 3” (80 mm) prior to addition of any fiber material. Fibers may also be added in loose form to aggregate charging devices.
- In all cases, consult the Safety Data Sheet before use.

DIRECTIONS FOR USE

PSI FIBERSTRAND REPREVE 225 fibers can be added to the concrete mixture at any time prior to placement of the concrete. It is generally recommended to add any fiber material to the concrete mixer during batching. Fibers must be mixed with concrete for a minimum of three to five (3-5) minutes at maximum mixing speed, depending upon the mixer type, to ensure complete dispersion and uniformity.

CLEAN UP

Loose fiber material may be disposed in proper receptacles for refuse. Finishing equipment with fibers embedded in concrete should be thoroughly cleaned.

Rev. 08.22

WARRANTY: The Euclid Chemical Company (“Euclid”) solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid’s installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid’s products for the Buyer’s intended purposes.